

# BLACKBUTT



## APPLICATIONS

FURNITURE, CABINETS, JOINERY, FLOORING, DECKING & CLADDING,

## DENSITY

900

## REGION

AUSTRALIA

Heartwood pale brown, but northern material may sometimes display a slight pinkish tinge. Sapwood distinctively paler. Texture medium and even. Grain usually straight. Gum veins are common.



# PROPERTIES

## DENSITY

900

## HARDNESS (JANKA) (KN)

9.0

## MACHINING

GOOD

## GLUING

POOR

## MODULUS OF ELASTICITY (GPA DRY)

19

## AVAILABILITY

WIDELY

## MODULUS OF RUPTURE (MPA DRY)

144

## FINISH

GOOD

## SCREWING SPLIT RESISTANCE

GOOD

## GROWING REGION

AUSTRALIA

## TANGENTIAL SHRINKAGE

7%

## SAPWOOD LYOTID SUSCEPTIBLE

NO

## RADIAL SHRINKAGE

4%

## DURABILITY

DURABLE

## NAILING SPLIT RESISTANCE

GOOD

## SPECIFIC GRAVITY

0.90

## STABILITY

GOOD